

**GLOBELL (HONG KONG) AGENCY LTD.**

Rm 10-11, 2/F, International Plaza,
No. 20 Sheung Yuet Road, Kowloon Bay, Hong Kong
Tel : 2751-6951 Fax : 2754-5018
e-mail : globell@netvigator.com

建议配方
外墙防水(起水珠)漆

原料成份	配方添加量
水	25.8
Karson GB 250BS(羟丙基多醣)	0.4
Prowell DA 8894(聚丙烯铵盐分散剂)	0.4
Prowell WA 8610(湿润剂)	0.2
Prowell DF 8890(有机硅消泡剂)	0.3
RTC-90(钛白粉)	17.5
CC-700(碳酸钙)	16.5
Sinocide DF 4041(防霉防藻剂)	1
Sinocide IC 1038(罐内防腐剂)	0.1
AMP 95(PH 稳定剂)	0.2
AC 261P(乳液)	32
Karson GB 005WD(水性蜡浆)	3
Texanol(异丁酸酯)	1.8
Prowell TA 2350(疏水聚氨增稠剂) ^②	0.6
Prowell DF 8890(有机硅消泡剂) ^②	0.2
Total	100